LONGi EcoLife

Define Roof Define Life

THE smarter E AWARD

S10 Double Glass Premium Black

(LR7-54HJBB)

490~505M 247W/m²

Leading
Black Module Efficiency

Efficiency 24.7%

70%
Output Maintained when Shaded[1]

Anti Shading

Highest
Fire Safety Report[2]

Class A Fire Rating

60°C+
Lower Temperature under Shade[3]

Prevent Overheating

High
Wind Resistance

Loading 6000/3600Pa

TIER 1 Bloomberg NEW ENERGY FINANCE

TÜV SÜD

CE

PV CYCLE

HIBC


30 YEAR WARRANTY Power | Product


Define Roof Define Life

LR7-54HJBB 490~505M

24.7%	0~3%	<1%	0.35%	BC-CELL
MAX MODULE EFFICIENCY	POWER TOLERANCE	FIRST YEAR POWER DEGRADATION	YEAR 2-30 POWER DEGRADATION	LOWER OPERATING TEMPERATURE


Additional Value





Mechanical Parameters

Cell Orientation	108 (6×18)
Junction Box	IP68
Output Cable	4mm², +400, -200mm/±1200mm length can be customized
Glass	Double glass 2.0mm semi-tempered glass+1.6mm semi-tempered glass
Frame	Black anodized aluminum alloy frame
Weight	23.5kg
Dimension	1800×1134×30mm
Packaging	36pcs per pallet / 216pcs per 20' GP / 864pcs per 40' HC



Electrical Characteristics

STC : AM1.5 1000W/m² 25°C

Test uncertainty for Pmax: ±3%

Module Type	LR7-54HJBB-490M	LR7-54HJBB-495M	LR7-54HJBB-500M	LR7-54HJBB-505M
Testing Condition	STC	STC	STC	STC
Maximum Power (Pmax/W)	490	495	500	505
Open Circuit Voltage (Voc/V)	41.25	41.35	41.45	41.55
Short Circuit Current (Isc/A)	15.04	15.15	15.26	15.37
Voltage at Maximum Power (Vmp/V)	34.07	34.17	34.27	34.37
Current at Maximum Power (Imp/A)	14.38	14.49	14.59	14.69
Module Efficiency(%)	24.0	24.3	24.5	24.7

Electrical characteristics with different rear side power gain (reference to 500W front)

Pmax /W	Voc/V	Isc /A	Vmp/V	Imp /A	Pmax gain
525	41.45	16.02	34.27	15.32	5%
550	41.45	16.78	34.27	16.05	10%
575	41.55	17.54	34.37	16.73	15%
600	41.55	18.31	34.37	17.46	20%
625	41.55	19.07	34.37	18.19	25%

Operating Parameters

Operational Temperature	-40°C ~ +85°C
Power Output Tolerance	0 ~ 3%
Maximum System Voltage	DC1500V (IEC)
Maximum Series Fuse Rating	30A
Nominal Operating Cell Temperature	45±2°C
Protection Class	Class II

Mechanical Loading

Front Side Maximum Static Loading	6000Pa
Rear Side Maximum Static Loading	3600Pa
Hailstone Test	25mm Hailstone at the speed of 23m/s

Temperature Ratings (STC)

Temperature Coefficient of Isc	+0.050%/°C
Temperature Coefficient of Voc	-0.210%/°C
Temperature Coefficient of Pmax	-0.240%/°C

LONGi

1. Data source:Test of single-cell shading in LONGi internal Lab. Anti-shading effect vary due to differences in test irradiation conditions, temperature, software, etc.
2. This product has obtained Class A fire test report. Due to various test factors, consistent results in every test cannot be guaranteed; actual test results prevail.
3. Data source: Comparison of test temperatures between EcoLife modules and conventional modules based on IEC 61215 Hot-spot endurance test (WBT) - MQT 09. Test data vary due to differences in the tested modules and institution.

Specifications included in this datasheet are subject to change without notice. LONGi reserves the right of final interpretation. (BGV02 20250905)